

- 1 -

Diaphragms for loudspeaker drive units

This invention relates to diaphragms for
loudspeaker drive units.

The construction of the diaphragm for a loudspeaker
5 drive unit involves a number of inter-related and often
conflicting criteria; in particular, the criteria of
mass, stiffness, cost, and sound transmission through the
diaphragm. In any given construction, these criteria
must be carefully balanced to make a successful
10 diaphragm; it is not generally possible to change any
one of them in a given construction without upsetting
the balance between them.

It is desirable to keep the mass of the diaphragm
low to achieve good sensitivity but it is difficult to
15 achieve a high degree of stiffness (which is desirable)
with a diaphragm of low mass.

Patent Specification DE 10049744 discloses the use
of polycrystalline diamond for making a diaphragm of
high stiffness and low mass but the cost and the
20 difficulty of fabrication preclude the use of diamond
other than for very small diaphragms.

Patent specification WO 00/78091 describes a
loudspeaker diaphragm made by winding tensile members
about a frame and providing a membrane on the tensile
25 members. A disadvantage of that construction is that

- 2 -

the diaphragm is relatively transparent to sound passing through the diaphragm. It would not, however, be desirable to add significantly to the mass in attempting to reduce the sound transmission through the diaphragm.

5 It has also been proposed to make a loudspeaker diaphragm using a foam material, see, for example, patent specification GB 2,059,717. Foam has the advantage of being light and resistant to the transmission of sound but has the disadvantage of not 10 having great stiffness. It would not, however, be desirable to add significantly to the mass in attempting to stiffen the diaphragm.

It is an object of the invention to provide a diaphragm for a loudspeaker drive unit which enables a 15 good balance between the criteria of mass, stiffness, cost and sound transmission through the diaphragm to be achieved.

The present invention provides a diaphragm for a loudspeaker drive unit, the diaphragm comprising a block 20 of material having a first, sound-radiating front face and a second, rear face, characterized in that the block is stiffened by being bound about over the first and second faces by a multiplicity of turns of one or more elongate members of flexible material stiffened by a 25 stiffening composition.

- 3 -

Such an arrangement is able to provide a diaphragm of improved performance without the need for a high degree of tension in the binding and without the need for a skin on the outside of the binding. High tension 5 in the binding may be used if desired and an outer skin may be provided if desired but it is preferred to use neither high tension nor an outer skin. The flexible nature of the material of the one or more elongate members makes it easy to wind about the block of 10 material and the stiffening composition imparts stiffness to the wound material and to the diaphragm as a whole.

Such a construction is able to provide good isolation of the delayed resonances which can arise when 15 the portion of the rear radiation of a loudspeaker diaphragm that is not absorbed by the speaker cabinet re-emerges through the diaphragm. That problem arises in conventional constructions because, typically, in a non-axisymmetric loudspeaker enclosure, the internal 20 sound field is diffuse and sound impinging on the rear of a conventional thin diaphragm is subject only to modest attenuation above the intrinsically low natural modes and, at certain frequencies, the transmission loss may be lower still without adequate damping.

- 4 -

The use of a block of the material as a diaphragm improves stiffness whilst avoiding the complexity of a composite "sandwich" construction involving thin elements. A "sandwich" construction is problematic 5 because the edges are difficult to deal with and, by its nature, the construction tends to be wasteful of materials.

Advantageously, the front face is convex. Such a construction avoids limitations of a simple conventional 10 cone diaphragm, namely, that the concave side of a cone can have a deleterious effect on both on the acoustic output of the cone itself as a result of cavity and horn type effects, and also on the output of neighbouring diaphragms as a result of cavity absorption and strong 15 reflection and re-radiation cancellation effects.

Advantageously, the second face is convex.

When the construction has two convex faces and is symmetrical, or at least approximately so, it overcomes the problem that a simple cone diaphragm is inherently 20 asymmetric at a normal to its central axis. This asymmetry of a conventional construction results in nonlinear distortion owing to the difference in radiation resistance of the cone moving forward to the cone moving backwards and the difference in axial

- 5 -

stiffness of the cone (loaded either by forcing acceleration or acoustic impedance) when the rim is being forced forwards or backwards.

The convex conical surfaces of the core may be
5 straight sided or may be radiused or may follow a hyperbolic or exponential profile.

The convex conical surfaces may be non-circular.

The convex conical surfaces of the foam core may be different in height and profile.

10 Preferably, the or each face is frusto-conical.

The block may be circular in front elevation.

Instead, the block may be elliptical in front elevation.

15 The block may be made of a rigid plastics foam material. The term "rigid plastics foam material" is used to distinguish from soft plastics foam material having effectively no structural strength.

Ideally, the foam should have as low a density as possible. In practice, the foam may have a density of
20 more than 20 grams per litre.

The foam may have a density between 28 and 35grams per litre.

Advantageously, the foam is a polymethyl methacrylamide foam.

- 6 -

Instead, the foam may be expanded polystyrene.

In an illustrated embodiment of the invention, the foam diaphragm core is of a very low density, largely non-porous foamed material with a relatively high 5 stiffness/mass ratio and high internal damping.

Polymethyl methacrylamide foam with a density of 30 grams/litre is a suitable material, or, for a reduced cost, a moulded expanded Polystyrene foam form of density around 30 grams/litre will suffice.

10 Advantageously, the block contains one or more internal voids. By this means, the mass of the diaphragm can be reduced.

Preferably, the one or more elongate members are in tension.

15 Preferably, the tension is a relatively low tension just sufficient to maintain the members taut at all times in use. Such a degree of tension is sufficient to allow proper bonding when it is desired that the one or more elongate members be bonded to the block of 20 material.

Advantageously, the or each elongate member is constituted by a bundle of monofilaments.

Preferably, the monofilaments are plastics material monofilaments.

- 7 -

The monofilament material may be paraphenylene polybenzobisoxazole.

The one or more flexible elongate members may comprise glass fibre monofilaments.

5 The body of material may be bound about by a single flexible elongate member.

Preferably, the diaphragm is a diaphragm for sub-bass or bass or bass-mid audio frequencies. Such diaphragms are relatively large and not difficult to
10 bind about with turns of the one or more flexible elongate members.

The body of material may be bound about by between 100 and 500 turns.

15 The body of material may be bound about by between 200 and 400 turns.

A protective rim may be provided at the periphery of the block between the one or more elongate members and the material of the block. Such a rim is particularly useful when the block of material is made
20 of polystyrene and liable to be too easily penetrated at its periphery by the one or more elongate members bound about it.

The one or more elongate members may be adhesively secured directly to the material of said block. The
25 stiffening composition may serve both to stiffen the one

- 8 -

or more elongate members and to secure them to the material of the block.

Preferably, the said first face of the block of the material and said one or more flexible members are 5 arranged to act directly on the ambient air to radiate sound. In such a construction, there is no additional skin to add unwanted mass to the diaphragm.

Advantageously, the diaphragm is bonded to a central tubular member for carrying the voice coil of 10 the loudspeaker drive unit.

The stiffening composition may comprise a resin composition.

The resin composition may be selected from the group consisting of a styrene resin, an epoxy resin, a 15 cellulose solvent based acrylic resin, a polyurethane resin, a cyanocrylate resin, and a thermosetting phenolic based resin.

The invention also provides a loudspeaker drive unit including a diaphragm as defined above.

20 The invention also provides a method of making a diaphragm for a loudspeaker drive unit, comprising binding a block of material with a multiplicity of turns of one or more elongate members of flexible material and using a stiffening composition to stiffen the one or 25 more elongate members.

- 9 -

Diaphragms for a loudspeaker drive unit constructed in accordance with the invention will now be described, by way of example only, with reference to the accompanying drawings, in which:

5

Figure 1 shows a diagrammatic cross-section through a loudspeaker drive unit including a diaphragm embodying the invention;

10

Figure 2 corresponds to Figure 1 but shows the provision of internal voids and a protective rim; and

Figure 3 is a perspective view of a diaphragm embodying the invention.

15

Referring to the accompanying drawings, Figure 1 shows a loudspeaker drive unit 1 embodying the invention. The drive unit comprises a chassis member 2 carrying a diaphragm suspension or surround 4. The surround, in turn, carries the diaphragm 6 of the loudspeaker drive unit. A central tube 8 is provided within the diaphragm 6. The loudspeaker drive unit 1 has a magnet assembly 10 and a suspension or "spider" 12 for the inner end of the tube 8. A voice coil is provided at the inner end of the tube 8 within the

- 10 -

magnet assembly 10 but is omitted from the drawings for ease of illustration.

The loudspeaker drive unit 1 is for the reproduction of sub-bass or bass or mid-bass audio 5 frequencies.

The diaphragm 6 is a shallow convex, symmetrical, lightweight diaphragm whose inherent rigidity and internal losses serve well to attenuate delayed resonances from inside a loudspeaker enclosure. The 10 tube 8 is a thin walled tube and can be either the loudspeaker voice coil former sleeve itself or can comprise an extension to a voice coil former sleeve.

Because of the presence of the tube 8 within the diaphragm 6, the diaphragm may be thought of as having a 15 very low relative density centre and may be thought of as described by the volume occupied by two conical surfaces placed edge to edge punctured by an axial bore hole whose diameter corresponds to the outer diameter of the tubular former. The tube 8 is, as shown, bonded 20 into the diaphragm, 6 so as to extend slightly beyond it.

In a practical example, the tube 8 was of a low density, high longitudinal stiffness material, in particular, tape-wound carbon fibre in an epoxy resin

- 11 -

composite with density 1.6 grams/cc and Young's modulus 300 GPa.

The ratio of the outer diameter of the diaphragm 6 to the diameter of the tube 8 is preferably 3:1. Most 5 practical constructions will lie between a ratio of 2:1 and a ratio of 6:1.

The ratio of the outer diameter of the diaphragm 6 to the overall thickness of the diaphragm is preferably 4:1. Most practical constructions will lie between a 10 ratio of 3:1 and 10:1.

The diaphragm 6 comprises a block of material having a first, sound-radiating front face 20 and a second, rear face 22. The block is stiffened by being bound about over the first and second faces 20, 22 by a 15 multiplicity of turns of an elongate member (not shown in Figures 1 and 2 for clarity of illustration) of flexible material and stiffened by a stiffening composition.

A single continuous fibre or tape is wound in 20 contact with and at a tangent to the slightly projecting tube 8, around the outside edge of the diaphragm 6 and back to the diametrically and vertically opposed tangential face of the tube whilst a synchronised periodic rotation of the diaphragm about its central

- 12 -

axis is performed. This operation is repeated for as many revolutions of the core as is required for an adequate covering of its surface. The method of winding is shown in Figure 4 of patent specification WO 5 00/78091. About 300 turns are put on the diaphragm 6.

Stiffening is achieved by the addition of an adhesive resin to the fibre as it is wound over the diaphragm 6 and tube 8, or by application of adhesive resin to the diaphragm and tube before the fibre is 10 wound, or by application of adhesive resin to the wound assembly of all three components by, for example, spraying. Such an adhesive resin can simply take the form of an automotive paint, for example, of an aesthetically pleasing colour. The following are all 15 suitable compositions for use: a two part styrene resin, a part epoxy resin, a cellulose solvent based acrylic lacquer, a two part isocyanate reactable lacquer, a part epoxy reactable lacquer, a polyurethane lacquer, a cyanoacrylate, and a thermosetting phenolic 20 based resin.

The front face 20 is convex and the second face 22 is also convex and the construction is symmetrical. The faces 20 and 22 are, as shown, frusto-conical. The diaphragm 6 is circular in front elevation.

- 13 -

The block of material constituting the diaphragm 6 is of a rigid plastics foam material. The foam is of a very low density, largely non-porous foamed material with a relatively high stiffness/mass ratio and high 5 internal damping. Polymethyl methacrylamide foam with a density of 30 grams/litre is a suitable material, or, for reduced cost, a moulded expanded polystyrene foam form of density around 30 grams/litre can be used.

In one practical example of the invention, the foam 10 material used was Rhoacell 31LS which has a density of 32 kg/m³ and a Young's modulus of 35 MPa. Rhoacell is available in different grades of different density and corresponding stiffness. For example, Rhoacell 51LS (density = 52 kg/m³, YM = 68MPa) and Rhoacell 71LS 15 (density = 75 kg/m³, YM = 90MPa). The diaphragm was machined from a solid block, Rhoacell being easy to machine although expensive.

The flexible elongate member is in tension but the tension is a relatively low tension just sufficient to 20 maintain the member taut at all times in use. The elongate member is constituted by a bundle of monofilaments of plastics material monofilaments. The elongate member is wound under sufficient tension to ensure that it remains taught over the whole structure,

- 14 -

in this way, all the available stiffness of the fibre
and the performance of the structure as a whole is
substantially maximised. It is possible, however, to
use a tension of a significantly higher to obtain a
5 degree of pre-stressing in the same manner of a spoked
wheel.

The elongate member is in contact with the foam core
and/or the tubular former at all times.

In one practical example, the elongate member was a
10 low density yet very high stiffness material with high
internal damping, in particular, monofilamentary
paraphenylene polybenzobisoxazole (PBO) Zylon HM tow
with a density of 1.56 grams/cc and a Young's modulus of
270 GPa. The lack of wastage in the construction and
15 the relatively small amount of material required almost
removes the need for any cheaper option but glass fibre
of density 2.7 g/cc and modulus 71GPa can produce
acceptable results in some applications.

Preferably, the fibres of the elongate member are
20 not only stiffened but are bonded to each other and the
diaphragm 6 and the tube 8.

In one practical example, the ratio of masses of
the three components tube 8, diaphragm 6 and elongate
member was 2:16:1. Most practical constructions will

- 15 -

lie within the ranges of the tube 8 being twice as heavy or half as light, or the elongate member being four times as heavy or half as light, both with respect to the diaphragm 6.

5 In one practical example, the diaphragm 6 had a 300mm outer diameter and the tube 8 a 100mm diameter. The elongate member had a diameter of about 0.07mm and about 300 turns were applied.

The illustrated construction has the advantage that
10 binding the diaphragm with the elongate member is able to shift the first break-up frequency of the diaphragm from 1500Hz to 2500Hz.

A modified embodiment of the invention is shown in Figure 2 in which identical reference numerals are used
15 for identical parts. Only the differences from the embodiment of Figure 1 will be described. In Figure 2, the diaphragm 6 includes an annular internal void 30 to reduce its mass. A circumferential protective rim 32 in the form of a ring of filament-wound carbon fibre
20 surrounds the periphery of the block of material constituting the diaphragm 6 and underlies the binding by the elongate member. The protective rim and internal void may be used independently as well as in conjunction with each other as illustrated.

- 16 -

Figure 3 shows a practical example of a diaphragm embodying the invention. The diaphragm of Figure 3 has an outer, metal mounting flange attached to the periphery of the surround 4 and a central dust cap 42, 5 for example, of woven carbon fibre is provided over the mouth of the tube 8. The elongate member bound about the diaphragm 6 is clearly to be seen as reference 36.

Instead of the dust cap shown in Figure 3, it is possible to provide a cylindrical plug of the foam 10 material within the interior of the tube 8.

The illustrated embodiments of the invention match the excellent axial mode performance of existing simple cone designs within similar overall dimensions, whilst addressing many of their limitations at a potentially 15 modest cost involving only a simple construction technique and little requirement for pre-processing of materials. The very small wastage in production and efficient use of materials allows greater use of more advanced components, in particular, the use of advanced, 20 high modulus fibres.

Alternative materials which can be used for the diaphragm 6 include Klegecell, Divinycell and Corecell, all of which are cheaper than Rhoacell but more difficult to machine.

- 17 -

Polystyrene is a very cheap alternative which can be injected moulded to form the desired shape for the diaphragm.

The diaphragm can, in fact, be made of virtually 5 any suitable lightweight material, for example, aluminium honeycomb, aramid honeycomb, metallic or ceramic foams, aerogels, syntactics, polymer moulded honeycombs or core structures, dimpled sheets, corrugated cardboard, glass microsphere composites, 10 endgrain or laminated balsa wood.

If desired, a thin membrane can be used to seal the block of material and a gas, other than air can be incorporated within the sealed block to improve the isolation from the inside to the outside of the 15 enclosure when the diaphragm is in use. Instead, by some form of pre-stressing of the bound diaphragm a vacuum can be sustained within it to provide the best acoustic isolation.

The elongate member can take the form of a 20 monofilament, yarn tow, wire, tape or ribbon and be of virtually any material. Cotton, silk, liquid crystal polymer, boron, shape memory metal, aramids and tungsten filaments can all be used.

- 18 -

The block of material used in the diaphragm may be a single block of integral construction or may be made from two or more smaller blocks joined together into a single block.

5 The invention is also applicable to a dome type speaker in which the tube carrying the voice coil is connected to the outside of the diaphragm.

In a construction using a central voice coil tube, it is possible to dispense with a tube that penetrates 10 the diaphragm and instead replace it by one which is bonded directly to the bottom of the inside edge of the diaphragm's central hole. The extra reinforcement to the strength of the diaphragm core that the illustrated construction imparts can be replaced or even exceeded by 15 changing the winding technique to toroidal winding.

Thus, a single continuous fibre can be wound down through the axial bore and over the diaphragm continuously until the whole structure is covered.

In the illustrated embodiments, the elongate member 20 is wound so that it is a tangent to the tube. This results in a distribution over the surface with greater fibre density, in terms of unit area, closer to the tube than towards the outer edge of the diaphragm. By altering the angle the fibre makes with the tube a more

- 19 -

uniform fibre distribution as regards to structural stiffness is possible.

Other suitable materials for the one or more elongate members are carbon fibre and Kevlar®.